



Tuyaux (plomberie, chauffage et usage général)Noirs et galvanisés
Black and galvanized steel pipe (plumbing, heating & general purpose)

Dimension Nominale/po Nominal size/inch	Dia. Ext. en pouces OD/inch	Ép. Paroi Cédule 5 Wall thickness sched. 5	Ép. Paroi Cédule 10 Wall thickness sched. 10	Ép. Paroi Cédule 40/STD Wall thickness sched. 40/STD	Ép. Paroi Cédule 80/XHV Wall thickness sched. 80/XHV
1/8	0.405	0.035	0.049	0.068	0.095
<i>Poids/pi</i>		<i>0.1383</i>	<i>0.1863</i>	<i>0.2447</i>	<i>0.3145</i>
1/4	0.540	0.049	0.065	0.088	0.119
<i>Poids/pi</i>		<i>0.257</i>	<i>0.3297</i>	<i>0.4248</i>	<i>0.5351</i>
3/8	0.675	0.049	0.065	0.091	0.126
<i>Poids/pi</i>		<i>0.3276</i>	<i>0.4325</i>	<i>0.5566</i>	<i>0.7388</i>
1/2	0.840	0.065	0.083	0.109	0.147
<i>Poids/pi</i>		<i>0.5358</i>	<i>0.6710</i>	<i>0.8510</i>	<i>1.088</i>
3/4	1.050	0.065	0.083	0.113	0.154
<i>Poids/pi</i>		<i>0.6838</i>	<i>0.8572</i>	<i>1.131</i>	<i>1.474</i>
1	1.315	0.065	0.109	0.133	0.179
<i>Poids/pi</i>		<i>0.8678</i>	<i>1.404</i>	<i>1.679</i>	<i>2.172</i>
1-1/4	1.660	0.065	0.109	0.140	0.191
<i>Poids/pi</i>		<i>1.107</i>	<i>1.806</i>	<i>2.273</i>	<i>2.997</i>
1-1/2	1.900	0.065	0.109	0.145	0.200
<i>Poids/pi</i>		<i>1.274</i>	<i>2.085</i>	<i>2.718</i>	<i>3.631</i>
2	2.375	0.065	0.109	0.154	0.218
<i>Poids/pi</i>		<i>1.604</i>	<i>2.638</i>	<i>3.653</i>	<i>5.022</i>
2-1/2	2.875	0.083	0.120	0.203	0.276
<i>Poids/pi</i>		<i>2.475</i>	<i>3.531</i>	<i>5.793</i>	<i>7.662</i>
3	3.500	0.083	0.120	0.216	0.300
<i>Poids/pi</i>		<i>3.029</i>	<i>4.332</i>	<i>7.576</i>	<i>10.25</i>
3-1/2	4.000	0.083	0.120	0.226	0.318
<i>Poids/pi</i>		<i>3.472</i>	<i>4.973</i>	<i>9.109</i>	<i>12.51</i>
4	4.500	0.083	0.120	0.237	0.337
<i>Poids/pi</i>		<i>3.915</i>	<i>5.631</i>	<i>10.79</i>	<i>14.98</i>
4-1/2	5.000	-	-	0.247	
<i>Poids/pi</i>		-	-	<i>12.53</i>	
5	5.563	0.109	0.134	0.258	0.375
<i>Poids/pi</i>		<i>6.349</i>	<i>7.770</i>	<i>14.62</i>	<i>20.78</i>
6	6.625	0.109	0.134	0.280	0.432
<i>Poids/pi</i>		<i>7.585</i>	<i>9.289</i>	<i>18.97</i>	<i>28.57</i>
7	7.625	-	-	0.301	
<i>Poids/pi</i>		-	-	<i>23.57</i>	
8	8.625	0.109	0.148	0.322	0.500
<i>Poids/pi</i>		<i>9.914</i>	<i>13.40</i>	<i>28.55</i>	<i>43.39</i>
9	9.625	-	-	0.342	0.500
<i>Poids/pi</i>		-	-	<i>33.90</i>	<i>48.72</i>
10	10.75	0.134	0.165	0.365	0.593/0.500
<i>Poids/pi</i>		<i>15.19</i>	<i>18.70</i>	<i>40.48</i>	<i>64.33/54.74</i>
11	11.75	-	-	0.375	0.500
<i>Poids/pi</i>		-	-	<i>45.55</i>	<i>60.07</i>
12	12.750	0.165	0.180	0.375	0.687/0.500
<i>Poids/pi</i>		<i>22.18</i>	<i>24.20</i>	<i>49.56</i>	<i>88.51/65.42</i>